

The apparatus is used for determining the Fineness Of Cement in terms of specific surface expressed as total surface area in square centimeters per gram of cement. The Blaine apparatus draws a defined volume of air through a prepared bed of cement of defined porosity. This is a variable flow type air permeameter.

STANDARD : ASTM C204, 88196-6



1. Air cylinder inner lumen diameter: $12.7 \pm 0.05 \text{ mm}$
2. Air cylinder inner lumen Sample height : $15 \pm 0.5 \text{ mm}$
3. Perforated plate hole number: 35PC
Perforated plate hole diameter: 1.0 mm
Perforated plate thickness: $1 - 0.10 \text{ mm}$
4. Voltage: 220V 50HZ
5. Net weight: 4 Kg

CST Instruments (Thailand) Co., Ltd.

Tel : 086-086-2000 / 02-915-1693

Tax ID : 0105566170152

95 Rom Klao Road, Khlong Sam Prawet, Lat Krabang, Bangkok 10520